

FASSON[®] Offset & Laser MC White FSC[®] Certified

Issued July 2024

Introduction

A premium-quality, machine-coated woodfree paper, semi-gloss, white.

Description

Face: A premium-quality, machine-coated woodfree, white paper with a semi-gloss finish. This product, FSC[®] C011032 certified, is sold as FSC[®] Mix Credit.

Availability

<i>Backing</i> ▼	<i>Adhesive</i> ▶	Permanent
No cracklines		x

Printing & Conversion

Offset printing.

Laserprinting/

Dry toner copiers: Suitable for most popular models. Tightly defined release characteristics avoid pre-dispensing during the printing process.

Inkjet printing: Some models of desktop inkjet printers have paper thickness limitations, which can cause feed problems.

Before applying the label, the surface must be clean, dry and grease-free.

Note: Please test the self-adhesive construction first to confirm compatibility.

Features: Excellent lay flatness, enabling high-speed printing
 Excellent guillotining and kiss-die cutting performance.
 Fast drying paper, enabling quick finishing (like cutting, die-cutting etc.)
 High temperature resistant adhesive enabling proper paper transport through dry toner copiers/-laser printers.

Recommendations for use

A variety of labels for: barcoding, addressing, inventory, product identification labels and other variably imprinted messages.

For indoor use.

General

Shelf life: 2 years stored at 20°C / 55%

R.H. Total caliper (±10 %): 164 micron

For information regarding EHS regulation, please visit our website under downloads “Technical bulletins“ TB 7.8 Product Compliance Fasson Offset” and for technical guidance “Technical bulletins“ – Offset printing.

PRODUCT CHARACTERISTICS

Physical properties

Face

Basis weight:	80 g/m ²	ISO 536
Caliper:	68 micron	ISO 534
Tensile:	5.2 kN/m MD	ISO 1924/2
Opacity:	87 %	ISO 2471

Adhesive

Permanent: General-purpose water-based permanent adhesive with a high initial tack and high adhesion on most common substrates.

Permanent

Adhesion (N/25mm) (FTM 1 on steel/20 min. bond time)	15.4
Tack(N) (FTM9 on st. steel)	10.3
Minimum application temperature	+5
Service temperature range after 24 hrs (°C)	+80
Resistance to cold (°C) ¹⁾ down to	-20

¹⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

Backing

No cracklines: A bleached one-side-coated white kraft, especially designed for sheet products, featuring minimal moisture sensitivity.

Basis weight:	80 g/m ²	ISO 536
Caliper:	81 micron	ISO 534

This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All products are sold subject to Torrapapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>. Fasson® and Crack-Back® are registered trademarks of Avery Dennison Corporation and related entities, and the products are produced by Torrapapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.